

KOPELEN JM-375
PP BLOCK COPOLYMER
General Information
Description

JM-375 is high impact block copolymer which has high ethylene-propylene rubber content. This grade is designed to be processed in conventional Injection molding equipment. JM-375 shows a high melt flow, controlled rheology and has good balance of strength, impact resistance, and processability.

Applications

- ◆ General supplies & Industrial supplies
- ◆ Automotive compound base resin

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ASTM D1238	45	g/10min		
Density	ASTM D792	0.90	g/cm³		
Mechanical					
Tensile Stress (Yield)	ASTM D638	260	kgf/cm²	25	MPa
Tensile Strain (Break)	ASTM D638	>100	%	>100	%
Flexural Modulus	ASTM D790	15,000	kgf/cm²	1,470	MPa
Impact					
Notched Izod Impact Strength (23℃)	ASTM D256	7.5	kgf-cm/cm	74	J/m
Notched Izod Impact Strength (-10℃)	ASTM D256	3.5	kgf-cm/cm	34	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm²)	ASTM D648	114	℃		
Additional Properties					
Flammability	UL94	-			

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

www.hpc.co.kr